

CONFIDENTIAL

**TEST REPORT ON DETERMINATION OF
RANDOM INCIDENCE SOUND ABSORPTION COEFFICIENT OF
FABRIC FACED GLASS FIBRE ACOUSTICAL PANEL**

NO. NVH/4831/2014-15/590(V-2)-5

DATE: 06.10.2014

- 1.0 CUSTOMER NAME :** Gyptech Systems
C-17, Miraj Apartments, Near Natubhai Centre
Race Course (W), Vadodara-390007
- 2.0 LETTER REF. :** E-mail dated 11th September 2014
- 3.0 TEST COMPONENT DETAILS :** Fabric faced glass fibre acoustical panel of
20 mm with following details given by customer:
- Surface : 60 GSM Non-woven fabric
 - Glass fibre : 20 mm and 96 kg/m²
 - Size of one panel : Fabric faced glass fibre acoustical panel of
595 mm X 595 mm
 - Absorbing material : 40 GSM Non-woven fabric
 - Type of mounting : Type E mounting with 300 mm air gap

4.0 TEST REQUIREMENTS :

Measurement of Random incidence sound absorption coefficient on above mentioned fabric faced glass fibre acoustical panel with 300 mm air gap as per ASTM C-423 in reverberation chamber.

5.0 TEST PROCEDURE :

The Random incidence sound absorption coefficient measurement was carried out on fabric faced glass fibre acoustical panel with 300 mm air gap as per ASTM C-423 in reverberation chamber. The test sample was mounted on the floor with Type E mounting. Please refer figure 1 for test set up and test component details. The measurement was carried out at temperature 25°C +/- 1°C and humidity 70%.

6.0 DATE OF EVALUATION :

The Random incidence sound absorption coefficient measurement was carried out on above mentioned fabric faced glass fibre acoustical panel on 27th September 2014.

Page 1 of 4

NO. NVH/4831/2014-15/590(V-2)-5

DATE: 06.10.2014

7.0 INSTRUMENTATION :

Sr. No	Instrument Name	Type / Model No	Make	Calibrated on	Calibration due on
1	Multi-channel Data Acquisition System	3560 D	Bruel & Kjaer, Denmark	30-Jul-14	30-Jul-15
2	½" Random Incidence Microphone	378B20 (Sr. No. 109015)	PCB, USA	10-Jun-14	10-Jun-15
3	Power Amplifier	2716	Bruel & Kjaer, Denmark	-	-
4	Omni directionnel sound source	Omni power 4296	Bruel & Kjaer, Denmark	-	-
5	Reverberation room	110 m ³	-	-	-

8.0 TEST RESULTS :

8.1 Table 1 shows the average values for random incidence sound absorption coefficient of Fabric faced glass fibre acoustical panel along with 300 mm air gap in the frequency range of 125 Hz to 5000 Hz.

8.2 Figure 2 shows the plot for random incidence sound absorption coefficient of Fabric faced glass fibre acoustical panel along with 300 mm air gap in the frequency range of 125 Hz to 5000 Hz.

9.0 CONCLUSIONS :

The Noise Reduction Coefficient (NRC) and Sound Absorption Average(SAA) is calculated as per ASTM C- 423	
Noise Reduction Coefficient (NRC)	0.90
Sound Absorption Average(SAA)	0.89

REPORT PREPARED BY:


MS. M. P. JOSHI
DY. MANAGER

REVIEWED BY:


S. K. JAIN
MANAGER

APPROVED BY:


N. V. KARANTH
SR. DEPUTY DIRECTOR & HOD

This test report pertains only to the samples actually tested at ARAI in the presented condition. The issuing of this test report does not indicate any measure of approval, certification, supervision, control of quality surveillance by ARAI of any product. No extract, abridgement or abstraction from this test report be published or used to advertise the product without the written consent of the Director, ARAI, who reserves the absolute right to agree or reject all or any of the details of any items of publicity for which consent may be sought.

NO. NVH/4831/2014-15/590(V-2)-5

DATE: 06.10.2014

Microphone
with rotating
boom

Omni
directional
source

Fabric faced
glass fibre
acoustical panel




Product Data

Material	Fabric Faced Glass Fibre Acoustical Panel
Size	595mm x 595mm
Thickness	20mm
Surface	60 GSM Nonwoven Fabric
Glass Fibre	20mm / 96kg/m ²
Edge Seal	20mm x 20mm G.I Angle Frame
Backing	40 GSM Nonwoven Fabric

Figure 1: Test set up for mounting and testing of Fabric faced glass fibre acoustical panel in reverberation chamber

Table 1 and Figure 2: Values and Plot for Random incidence sound absorption coefficient of Fabric faced glass fibre acoustical panel tested along with E-300 configuration

One third octave frequency, Hz	Random Incidence Sound Absorption Coefficient
125	0.60
160	0.98
200	0.93
250	0.98
315	0.92
400	0.85
500	0.80
630	0.79
800	0.86
1000	0.87
1250	0.88
1600	0.94
2000	0.90
2500	0.92
3150	0.91
4000	0.91
5000	0.92



Note: (*)Measurement uncertainty for Random incidence sound absorption coefficient evaluation is $\pm 7\%$ at 95.45% confidence level and $k = 2$ in the frequency range 125 Hz to 5000 Hz)